

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : H01G 9/20	A1	(11) International Publication Number: WO 97/08719 (43) International Publication Date: 6 March 1997 (06.03.97)
(21) International Application Number: PCT/US96/13132 (22) International Filing Date: 13 August 1996 (13.08.96) (30) Priority Data: 08/519,474 25 August 1995 (25.08.95) US (71) Applicant: VALENCE TECHNOLOGY, INC. [US/US]; 301 Conestoga Way, Henderson, NV 89015 (US). (72) Inventor: SHACKLE, Dale, R.; 17135 Oak Leaf Drive, Morgan Hill, CA 95037 (US). (74) Agent: KREBS, Robert, E.; Burns, Doane, Swecker & Mathis, L.L.P., P.O. Box 1404, Alexandria, VA 22313-1404 (US).		(81) Designated States: AL, AM, AT, AU, AZ, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, UZ, VN, ARIPO patent (KE, LS, MW, SD, SZ, UG), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: PHOTOELECTROCHEMICAL CELL (57) Abstract This invention is directed to a photoelectrochemical cell having increased conductivity. The cell employs an electrolyte formed from a polymeric matrix, an electrolytic solvent, an inorganic ion salt and a redox couple.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

PHOTOELECTROCHEMICAL CELL

BACKGROUND OF THE INVENTION

5

Field of the Invention

This invention is directed to solid electrolytes containing a polymer matrix and an electrolyte solvent (plasticizer) for the polymer matrix. This invention is further directed to a photoelectrochemical cell employing the polymer matrix.

10

State of the Art

Photoelectrochemical cells are photovoltaic devices based on the junction of a semiconductor photoelectrode and an electrolyte containing a redox couple, such as $I/I_3^-/I_2$ or $S^{2-}/S^{2-}/S_{x+1}^{2-}$. These systems have heretofore generally employed n-type semiconductors and transparent electrodes. Illumination produces photogenerated holes that oxidize the complex anions in the electrolyte solution, while electrons travel from the semiconductor through an external load to reduce the species at the transparent illuminated surface. Rediffusion in the electrolyte of the species completes the electrochemical cycle.

15

20

Polymeric electrolytes such as polyethylene oxide (PEO) have been used in photoelectrochemical cells to eliminate corrosion and side reactions of the semiconductor/electrolyte interface which are commonly observed with conventional electrolyte solvents.

25

However, cells with PEO electrolytes have relatively low conductivity and hence low efficiency. See Gray, "Solid Polymer Electrolytes; Fundamentals and Technological Applications," VCH Publishers, 1991, pp 28-29.

30

There is thus a need in the art for an electrolyte for a photoelectrochemical cell having increased conductivity but retaining the resistance to corrosion and side reactions of PEO.

5

SUMMARY OF THE INVENTION

The present invention is directed, in part, to the discovery that the use of certain solid electrolytes in the manufacture of photoelectrochemical cells can enhance conductivity compared to known cells, particularly with respect to those cells using polyethylene oxide (PEO) electrolytes. In addition, the use of the solid electrolytes of the invention provides increased transparency which aids in photocell efficiency.

Accordingly, in a composition aspect, the present invention is directed to a photoelectrochemical cell which comprises: a current collector, a semiconductor secured on one side to the current collector, a single phase, solid solvent-containing electrolyte secured to the other side of the semiconductor, and a transparent electrode secured to the solid electrolyte on a side opposite from the semiconductor, wherein the solid electrolyte comprises a redox couple, a solid polymeric matrix, an inorganic ion salt, and an electrolytic solvent.

20

In one of its method aspects, the present invention is directed to a method for enhancing the conductivity of a photoelectrochemical cell which comprises incorporating in the cell the solid, single- phase, solvent-containing electrolyte described above.

25

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

As noted above, this invention is directed to photoelectrochemical cells containing solid, solvent-containing electrolytes.

30

The solid electrolytes of the invention contain either an inorganic or an organic matrix and a suitable inorganic ion salt as a separate component. The

inorganic matrix may be non-polymeric (e.g., β -alumina, silver oxide, lithium iodide, etc.) or polymeric (e.g., inorganic (polyphosphazene) polymers) whereas the organic matrix is typically polymeric. Suitable organic polymeric matrices are well known in the art and are typically organic polymers obtained by
5 polymerization of a suitable organic monomer as described, for example, in U.S. Patent No. 4,908,283. Suitable organic monomers include, by way of example, ethylene oxide, propylene oxide, ethyleneimine, epichlorohydrin, ethylene succinate, and an acryloyl-derivatized polyalkylene oxide containing an acryloyl group of the formula $\text{CH}_2=\text{CR}'\text{C}(\text{O})\text{O}-$ where R' is hydrogen or lower alkyl of from 1-6
10 carbon atoms.

Because of their expense and difficulty in forming into a variety of shapes, inorganic non-polymeric matrices are generally not preferred, rather, a solid electrolyte containing a polymeric matrix is typically employed. In order to
15 maximize the conductivity of solid electrolytes having a polymeric matrix, the latter is generally constructed into a very thin film, i.e., on the order of about 25 to about 250 μm . As is apparent, the reduced thickness of the film reduces the total amount of internal resistance within the electrolyte thereby minimizing losses in conductivity due to internal resistance.

20 The solid electrolytes also contain a solvent (plasticizer) which is added to the matrix primarily in order to enhance the solubility of the inorganic ion salt in the solid electrolyte and thereby increase the conductivity of the photoelectrochemical cell. In this regard, the solvent requirements of the solvent
25 used in the solid electrolyte have been art recognized to be different from the solvent requirements in liquid electrolytes. For example, solid electrolytes require a lower solvent volatility as compared to the solvent volatilities permitted in liquid electrolytes.

30 Suitable solvents well known in the art for use in such solid electrolytes include, by way of example, propylene carbonate, ethylene carbonate, γ -

butyrolactone, tetrahydrofuran, glyme (dimethoxyethane), diglyme, triglyme, tetraglyme, dimethylsulfoxide, dioxolane, sulfolane and the like.

5 The solid, solvent-containing electrolyte is typically formed by one of two methods. In one method, the solid matrix is first formed and then a requisite amount of this material is dissolved in a volatile solvent. Requisite amounts of the inorganic ion salt and the electrolyte solvent (usually a glyme and the organic carbonate) are then added to the solution. This solution is then placed on the surface of a suitable substrate (e.g., the surface of a semiconductor) and the
10 volatile solvent is removed to provide for the solid electrolyte.

 In the other method, a monomer or partial polymer of the polymeric matrix to be formed is combined with appropriate amounts of the inorganic ion salt and the solvent. This mixture is then placed on the surface of a suitable substrate
15 (e.g., the surface of the semiconductor) and the monomer is polymerized or cured (or the partial polymer is then further polymerized or cured) by conventional techniques (heat, ultraviolet radiation, electron beams, etc.) so as to form the solid, solvent-containing electrolyte.

20 Prior to describing this invention in further detail, the following terms will first be defined.

Definitions

As used herein, the following terms have the following meanings.

25

 The term "solid polymeric matrix" refers to an electrolyte compatible material formed by polymerizing an inorganic or organic monomer (or partial polymer thereof) and which, when used in combination with the other components of the electrolyte, renders the electrolyte solid. The solid matrix may or may not
30 be ion-conducting.

Suitable solid polymeric matrices are well known in the art and include solid matrices formed from inorganic polymers, organic polymers or a mixture of organic polymers with inorganic non-polymeric materials. Preferably, the solid polymeric matrix is an organic matrix derived from a solid matrix forming monomer and/or from partial polymers of a solid matrix forming monomer.

Alternatively, the solid polymeric matrix can be used in combination with a non-polymeric inorganic matrix. See, for example, U.S. Patent No. 4,990,413, which is incorporated herein by reference in its entirety. Suitable non-polymeric inorganic materials for use in conjunction with the solid polymeric matrix include, by way of example, β -alumina, silver oxide, lithium iodide, and the like. Suitable inorganic monomers are also disclosed in U.S. Patent Nos. 4,247,499; 4,388,385; 4,414,607; 4,394,280; 4,432,891; 4,539,276; and 4,557,985 each of which is incorporated herein by reference.

The term "a solid matrix forming monomer" refers to inorganic or organic materials which in monomeric form can be polymerized, preferably in the presence of an inorganic ion salt, and an electrolytic solvent to form solid matrices which are suitable for use as solid electrolytes in photoelectrochemical cells. Suitable solid matrix forming monomers are well known in the art and the particular monomer employed is not critical. Preferably, the solid matrix forming monomers have at least one heteroatom capable of forming donor acceptor bonds with inorganic cations (e.g., alkali ions). When polymerized, such compounds form an ionically conductive matrix.

Examples of suitable organic solid matrix forming monomers include, by way of example, propylene oxide, ethyleneimine, ethylene oxide, epichlorohydrin, acryloyl-derivatized polyalkylene oxides (as disclosed in U.S. Patent No. 4,908,283), vinyl sulfonate polyalkylene oxides (as disclosed in U.S. Patent 5,262,253, which patent is incorporated herein by reference in its entirety), and

the like as well as mixtures thereof. Ethylene oxide is especially preferred in combination with acrylate end groups.

5 Examples of suitable inorganic solid matrix forming monomers include, by way of example, phosphazenes and siloxanes. Phosphazene monomers and the resulting polyphosphazene solid matrix are disclosed by Abraham et al., Proc. Int. Power Sources Symp., 34th, pp. 81-83 (1990) and by Abraham et al., J. Electrochemical Society, Vol. 138, No. 4, pp. 921-927 (1991).

10 The term "a partial polymer of a solid matrix forming monomer" refers to solid matrix forming monomers which have been partially polymerized to form reactive oligomers. Partial
polymerization may be conducted for the purpose of enhancing the viscosity of the monomer, decreasing the volatility of the monomer, and the like. Partial
15 polymerization is generally permitted so long as the resulting partial polymer can be further polymerized to form solid polymeric matrices which are suitable for use as solid electrolytes in photoelectrochemical cells.

20 The term "cured" or "cured product" refers to the treatment of the solid matrix forming monomer or partial polymer thereof under polymerization conditions (including cross-linking) so as to form a solid polymeric matrix. Suitable polymerization conditions are well known in the art and include by way of example, heating the monomer, irradiating the monomer with UV light, electron beams, etc. The resulting cured product preferably contains repeating units containing at least one heteroatom such as oxygen or nitrogen which is capable of
25 forming donor acceptor bonds with inorganic cations (e.g., alkali ions). Examples of suitable cured products suitable for use in this invention are set forth in U.S. Patent Nos. 4,830,939 and 4,990,413 which are incorporated herein by reference in their entirety.

30

The solid matrix forming monomer or partial polymer can be cured or further cured prior to or after addition of the solvent. For example, a composition comprising requisite amounts of the solid matrix forming monomer, electrolyte solvent and inorganic ion salt can be applied to a substrate and then cured.

5 Alternatively, the solid matrix forming monomer can be first cured and then dissolved into a suitable volatile solvent. Requisite amounts of the solvent and inorganic ion salt can then be added. The mixture is then placed on a substrate and removal of the volatile solvent results in formation of a solid electrolyte. In

10 either case, the resulting solid electrolyte is a homogeneous, single phase product which is maintained upon curing, and does not readily separate upon cooling to temperatures below room temperature. Accordingly, the solid electrolyte of this invention does not include a separator as is typical of liquid electrolytes.

The term "inorganic ion salt" refers to any inorganic salt which is suitable

15 for use in a solid electrolyte. Representative examples are alkali metal salts of less mobile anions of weak bases having a large anionic radius. Examples of such anions are I^- , Br^- , SCN^- , ClO_4^- , BF_4^- , PF_6^- , AsF_6^- , CF_3COO^- , $CF_3SO_3^-$, etc. Specific examples of suitable inorganic ion salts include $LiClO_4$, LiI , $LiSCN$, $LiBF_4$, $LiAsF_6$, $LiCF_3SO_3$, $LiPF_6$, NaI , $NaSCN$, KI , and the like. The inorganic

20 ion salt preferably contains at least one atom of Li, Na, K or Mg.


The term "organic carbonate" refers to hydrocarbyl carbonate compounds of no more than about 12 carbon atoms and which do not contain any hydroxyl groups. Preferably, the organic carbonate is a linear aliphatic carbonate or a

25 cyclic aliphatic carbonate.

In a more preferred embodiment, the carbonate is a cyclic aliphatic carbonate represented by the formula:

8

5



10

where each of R_1 , R_2 , R_3 , R_4 , R_5 , and R_6 are independently selected from the group consisting of hydrogen and alkyl of 1 or 2 carbon atoms, and m is an integer equal to 0 or 1.

15

In a particularly preferred embodiment, m is equal to zero and R_1 , R_2 , and R_5 are hydrogen and R_6 is hydrogen (ethylene carbonate), $-CH_3$ (propylene carbonate) or $-CH_2CH_3$ (butylene carbonate).

20

Suitable cyclic aliphatic carbonates for use in this invention include 1,3-dioxolan-2-one (ethylene carbonate); 4-methyl-1,3-dioxolan-2-one (propylene carbonate); 4,5-dimethyl-1,3-dioxolan-2-one; 4-ethyl-1,3-dioxolan-2-one; 4,4-dimethyl-1,3-dioxolan-2-one; 4-methyl-5-ethyl-1,3-dioxolan-2-one; 4,5-diethyl-1,3-dioxolan-2-one; 4,4-diethyl-1,3-dioxolan-2-one; 1,3-dioxan-2-one; 4,4-dimethyl-1,3-dioxan-2-one; 5,5-dimethyl-1,3-dioxan-2-one;

25

5-methyl-1,3-dioxan-2-one; 4-methyl-1,3-dioxan-2-one; 5,5-diethyl-1,3-dioxan-2-one; 4,6-dimethyl-1,3-dioxan-2-one; 4,4,6-trimethyl-1,3-dioxan-2-one; and spiro[1,3-oxa-2-cyclohexanone-5',5',1',3'-oxa-2'-cyclohexanone].

30

Several of these cyclic aliphatic carbonates are commercially available such as propylene carbonate and ethylene carbonate. Alternatively, the cyclic aliphatic

carbonates can be readily prepared by well known reactions. For example, reaction of phosgene with a suitable alkane- α,β -diol (dihydroxy alkanes having hydroxyl substituents on adjacent carbon atoms) or an alkane- α,γ -diol (dihydroxy alkanes having hydroxyl substituents on carbon atoms in a 1,3 relationship) yields
5 an a cyclic aliphatic carbonate for use within the scope of this invention. See, for instance, U.S. Patent No. 4,115,206, which is incorporated herein by reference in its entirety.

Likewise, the cyclic aliphatic carbonates useful for this invention may be
10 prepared by transesterification of a suitable alkane- α,β -diol or an alkane- α,γ -diol with, e.g., diethyl carbonate under transesterification conditions. See, for instance, U.S. Patent Nos. 4,384,115 and 4,423,205 which are incorporated herein by reference in their entirety.

15 Additional suitable cyclic aliphatic carbonates are disclosed in U.S. Patent No. 4,747,850 which is also incorporated herein by reference in its entirety.

In a more preferred embodiment, linear aliphatic carbonates are represented by the formulae:

20



where each R_7 and R_8 are independently selected from the group consisting of alkyl of from 1 to 4 carbon atoms; R_9 is an alkylene group of from 2 to 4 carbon atoms;

25 t is an integer of 1 or 2, and u is an integer from 1 to 4.

Most preferably, the linear aliphatic carbonate is a carbonate of the formula:

30



where R_7 , R_8 and t are as defined above.

Linear aliphatic carbonates are well known in the art and a variety of which are commercially available. Additionally, the linear aliphatic carbonates can be prepared by transesterification of a suitable alcohol (e.g., R_7OH or R_8OH) with, e.g., diethyl carbonate under transesterification conditions.

The term "glyme" refers to ethylene glycol dimethyl ether or $CH_3OCH_2CH_2OCH_3$. The term "a glyme" refers to glyme and also to diglyme, triglyme, tetraglyme, etc., which contain repeating units of $-(OCH_2CH_2)-$.

The term "photoelectrochemical cell" refers to a composite that comprises a current collector, a semiconductor, the solid electrolyte, and a transparent electrode.

15

The term "urethane acrylate" refers to urethane diacrylate.

Methodology

Methods for preparing solid, solvent-containing electrolytes are well known in the art. As noted above, various organic carbonates are either commercially available or can be prepared by art recognized methods. Preferably, the solvent includes a glyme.

The solid, solvent-containing electrolyte is preferably prepared by combining one or more solid matrix-forming monomers, and an inorganic ion salt. The resulting composition is then uniformly coated onto a suitable substrate (e.g., a semiconductor or transparent electrode) by means of a roller, a doctor blade, a bar coater, a silk screen or spinner to obtain a film of this composition or its solution. In some cases, it may be necessary to heat the composition so as to provide for a coatable material.

Preferably, the amount of material coated onto the substrate is an amount sufficient so that after curing, the resulting solid, solvent-containing electrolyte has a thickness of no more than about 250 microns (μm). Preferably, the solid, solvent-containing electrolyte may have a thickness of from about 20 to about 250
5 microns. The final thickness will depend on the particular application.

The electrolyte composition typically comprises from about 5 to about 25 weight percent of the inorganic ion salt based on the total weight of the electrolyte; preferably, from about 10 to 20 weight percent; and even more preferably from
10 about 10 to about 15 weight percent.

The electrolyte composition typically comprises from about 40 to about 80 weight percent solvent (e.g., organic carbonate/glyme mixture) based on the total weight of the electrolyte; preferably from about 60 to about 80 weight percent; and
15 even more preferably about 70 weight percent.

The solid electrolyte composition typically comprises from about 5 to about 30 weight percent of the solid polymeric matrix based on the total weight of the electrolyte; preferably from about 15 to about 25 weight percent.
20

In a preferred embodiment, the electrolyte composition further comprises a small amount of a film forming agent. Suitable film forming agents are well known in the art and include, by way of example, polyethylene oxide, polypropylene oxide, copolymers thereof, and the like, having a numbered average
25 molecular weight of at least about 100,000. The polyethylene oxide or polypropylene oxide film forming agent, if present, is in an amount which does not significantly lower the conductivity of the electrolyte. Preferably, the film forming agent is employed in an amount of about 1 to about 10 weight percent and more preferably at about 2.5 weight percent based on the total weight of the electrolyte
30 composition.

The composition is cured by conventional methods to form a solid film. For example, when the solid matrix forming monomer contains a reactive double bond, suitable curing methods include heating, irradiation with UV radiation, irradiation with electron beams (EB), etc. When the composition is cured by
5 heating or UV radiation, the composition preferably contains an initiator. For example, when curing is by heating, the initiator is typically a peroxide such as benzoyl peroxide, methyl ethyl ketone peroxide, t-butyl peroxypropionate, diisopropyl peroxydicarbonate, and the like. When curing is by UV radiation, the initiator is typically benzophenone, Darocur 1173 (Geigy, Ardsley, New York),
10 and the like.

The initiator is generally employed in an amount sufficient to catalyze the polymerization reaction. Preferably, the initiator is employed at up to about 1 weight percent based on the weight of the solid matrix forming monomer.

15

When curing is by EB treatment, an initiator is not required.

The resulting solid electrolyte is a homogeneous, single phase material which is maintained upon curing, and does not readily separate upon cooling to
20 temperatures below room temperature. See, for example, U.S. Patent No. 4,925,751 which is incorporated herein by reference in its entirety.

Additionally, it is desirable to avoid the use of any protic materials which will be incorporated into the photoelectrochemical cell. For example, most of the
25 protic inhibitors in mono-, di-, tri- and higher functional acrylate monomers as well as in the urethane acrylate prepolymers, are preferably removed prior to formation of the cathode and/or electrolyte. In this regard, removal of these inhibitors down to a level of less than 50 parts per million (ppm) can be accomplished by contacting these monomers and prepolymers with an inhibitor remover.
30 Suitable inhibitor removers are commercially available.

In a preferred embodiment, the process of forming a photoelectrochemical cell comprises the steps of securing a semiconductor to a current collector. Thereafter, a composition comprising at least one solid matrix forming monomer, an inorganic ion salt and the solvent, for example, a mixture of an organic carbonate and a glyme compound, is applied to the opposite side of the semiconductor. The composition is then cured to provide for a solid electrolyte on the semiconductor surface. A transparent electrode is then laminated to this composite product in such a way that the solid electrolyte is interposed between the transparent electrode and the semiconductor.

10

This process can be reversed, so that the surface of the transparent electrode is coated with a composition comprising a solid matrix forming monomer, the solvent or solvent mixture and an inorganic salt. The composition is then cured to provide for a solid electrolyte on the electrode surface. The semiconductor and current collector are then laminated to this composite product in such a way that the solid electrolyte is interposed between the transparent electrode and the semiconductor.

15

Methods for preparing solid electrolytes are also set forth in U.S. Patent Nos. 4,830,939 and 4,925,751 which are incorporated herein by reference in their entirety.

20

Utility

The solid, solvent-containing electrolytes described herein are particularly useful in preparing solid photoelectrochemical cells.

25

The cells of the invention have increased conductivity compared with photoelectrochemical cells of the prior art using polyethylene oxide electrolyte.

30

The following examples are offered to illustrate the present invention and should not be construed in any way as limiting its scope.

EXAMPLE 1

A. Semiconductor

An n-type semiconductor available from Cerac, Milwaukee, Wisconsin is used in making the cell.

5

B. Electrolyte

The electrolyte may be prepared by first combining 56.51 grams of propylene carbonate, 14.13 grams triglyme and 17.56 grams of urethane acrylate (available as Photomer 6140 from Henkel Corporation, Coating and Chemicals Division, Ambler, PA). The propylene carbonate/triglyme/urethane acrylate mixture is dried over molecular sieves (Grade 514, 4Å, 8-12 mesh, available from W. R. Grace, Baltimore, MD) to remove water.

10

This solution is then combined with 2.56 grams of poly-ethylene oxide (weight average molecular weight about 600,000 available as Polyox WSR-205 from Union Carbide Chemicals and Plastics, Danbury, CT). The resulting mixture is thoroughly mixed with the same laboratory mixer at heating until a temperature of about 65°C is reached and then cooled to ambient temperature over at least a 2 hour period while stirring is maintained.

20

Once the polyethylene oxide is dispersed and dissolved, 9.24 grams of LiAsF₆ (available from FMC Corporation Lithium Division, Bessemer City, NC, as Lectrosalt®) and are added while stirring with a laboratory mixer (Yamato Model LR41B, available from Fisher Scientific, Santa Clara, CA). A redox couple consisting of 1.0 g LiI and 0.1 g I₂ are then added.

25

The resulting 100 gram mixture would contain the following weight percent of components:

15

	Propylene carbonate	56.51 weight percent
	Triglyme	14.13 weight percent
	Urethane acrylate (Photomer 6140)	16.46 weight percent
	LiAsF ₆	9.24 weight percent
5	Polyethylene oxide	2.56 weight percent
	LiI	1.0 g weight percent
	I ₂	0.1 g weight percent

Afterwards, the electrolyte mixture is then coated by a conventional knife
10 blade to a thickness of about 50 μ m onto the surface of the cathode/semiconductor
sheet prepared as above (on the side having the semiconductor) but without the
Mylar covering. The electrolyte is then cured by continuously passing the sheet
through an electron beam apparatus (Electrocurtain, Energy Science Inc., Woburn,
MA) at a voltage of about 175 kV and a current of about 1.0 mA and at a
15 conveyor speed setting of 50 which provides for a conveyor speed of about 1
cm/sec. After curing, a composite is recovered which contains a solid electrolyte
laminated to semiconductor which, in turn, is laminated to a nickel on nickel
current collector.

An alternative method of fabricating the electrolyte is as follows:

20

35.71 grams of propylene carbonate, 3.45 grams of trimethyl propyl
triacrylate, 35.71 grams of ethylene carbonate, and 13.79 grams of urethane
acrylate (Actilane SP023, available from Akcros Chemicals, Ltd., Manchester,
England) are combined at room temperature until homogeneous. The resulting
25 solution is optionally passed through a column of 4A molecular sieves to remove
water and then the recovered solution is mixed at room temperature until
homogeneous. If necessary, the ethylene carbonate can first be dissolved in
propylene carbonate with heat.

30

At this point, 1.47 grams of polyethylene oxide film forming agent having
a number average molecular weight of about 600,000 (available as Polyox WSR-
205 from Union Carbide Chemicals and Plastics, Danbury, CT) is added to the
above solution and then dispersed while stirring with a magnetic stirrer over a

16

period of about 60 - 120 minutes. After dispersion, the solution is heated to between 60° and 65°C with stirring until the film forming agent is dissolved. A thermocouple is placed at the edge of the vortex created by the magnetic stirrer to monitor solution temperature. The solution is cooled to a temperature of less than 48°C and then 8.77 grams of LiPF_6 are added to the solution over a 120 minute period while thoroughly mixing to ensure a substantially uniform temperature profile throughout the solution. A redox couple consisting of 1.0 grams LiI and 0.1 grams I_2 are also added. Cooling is applied as necessary to maintain the temperature of the solution at less than 48°C.

In one optional embodiment, the polyethylene oxide film forming agent is added to the solution via a mini-sieve, such as a 25 mesh mini-sieve that is commercially available as Order No. 57333-965 from VWR Scientific, San Francisco, CA.

The resulting solution contains the following (in approximate weight percent based on the total weight of the electrolyte solution (100 g):

20	Propylene Carbonate	35.71 %
	Ethylene Carbonate	35.71 %
	Trimethylol propyl triacrylate (TMPTA)	3.45 %
	Urethane Acrylate	13.79 %
	LiPF_6	8.77 %
25	PEO Film Forming Agent	1.47 %
	LiI	1.00 %
	I_2	<u>0.10 %</u>
	Total	100 %

This solution is then degassed to provide for an electrolyte solution wherein little, if any, of the LiPF_6 salt decomposes.

Optionally, the above solution which contains the prepolymer, the film forming agent, the electrolytic solvent, the LiPF_6 salt and the redox couple, is filtered to remove any solid particles or gels remaining in the solution. One suitable filter device is a sintered stainless steel screen having a pore size between
5 1 and 50 μm at 100% efficiency.

In an alternative embodiment, the electrolyte is prepared by the following steps using the same above described electrolyte components:

10 1. Check the moisture level of the urethane acrylate. If the moisture level is less than 100 ppm water, proceed to step 2. If not, then first dissolve the urethane acrylate at room temperature, $<30^\circ\text{C}$, in the propylene carbonate and ethylene carbonate and dry the solution over 4A molecular sieves (Grade 514, 8-12 Mesh from Schoofs Inc., Moraga, CA) and then proceed to step
15 4.

2. Dry the propylene carbonate and ethylene carbonate over 4A molecular sieves (Grade 514, 8-12 Mesh from Schoofs Inc., Moraga, CA).

20 3. At room temperature, $<30^\circ\text{C}$, add the urethane acrylate to the solvent prepared in step 2. Stir until the resin is completely dissolved. The solution should be clear and colorless.

4. Dry and optionally sift the polyethylene oxide film forming
25 agent through a 25 mesh mini-sieve commercially available as Order No. 57333-965 from VWR Scientific, San Francisco, CA. While stirring add the dried and pre-sifted polyethylene oxide film forming agent slowly to the solution. The polyethylene oxide film forming agent should be sifted into the center of the vortex formed by the stirring means at a controlled rate to avoid agglomerate formation.
30 Addition of the polyethylene oxide film forming agent should be dispersive and,

during addition, the temperature should be maintained at room temperature (<30°C).

5 5. After final addition of the polyethylene oxide film forming agent, stir to ensure that the film forming agent is substantially dispersed.

 6. Heat the mixture to 68° to 75°C and stir until the film forming agent has melted and the solution has become transparent. Optionally, in this step, the mixture is heated to 65° to 68°C.

10 7. Cool the solution produced in step 6 and when the temperature of the solution reaches 40°C, add the LiPF₆ salt and redox couple very slowly making sure that the maximum temperature does not exceed 55°C and preferably does not exceed about 40°C.

15 8. Following the addition of the LiPF₆ salt and redox couple, the solution is stirred and degassed. The electrolyte solution is allowed to cool before usage.

20 9. Optionally, filter the solution through a sintered stainless steel screen having a pore size between 1 and 50 μm at 100% efficiency.

 At all times, the temperature of the solution should be monitored with a thermocouple which should be placed in the vortex formed by the mixer.

25

C. The Photoelectrochemical Cell

 The photoelectrochemical cell is prepared by applying the n-type semiconductor onto one side of a current collector. An electrolyte composition as described above is then placed onto the other side of the semiconductor and cured to provide for the solid electrolyte. Then, an indium tin oxide (ITO) transparent electrode is laminated onto the solid electrolyte to provide for the

30

19

photoelectrochemical cell. The ITO transparent electrode is formed by coating ITO by vacuum deposition onto a piece of glass. A protective layer of glass is then secured over the transparent electrode.

5 Although only preferred embodiments of the invention are specifically disclosed and described above, it will be appreciated that many modifications and variations of the present invention are possible in light of the above teachings and within the purview of the appended claims without departing from the spirit and intended scope of the invention.

10

WHAT IS CLAIMED IS:

1. A photoelectrochemical cell which comprises:
a current collector;
5 a semiconductor secured on one side to the current collector;
a transparent single phase, solid solvent-containing electrolyte
secured to the other side of the semiconductor; and
a transparent electrode secured to the solid electrolyte on a
side opposite from the semiconductor;
10 wherein the solid electrolyte comprises a redox couple, a
solid, polymeric matrix, an inorganic ion salt, and a non-aqueous electrolytic
solvent.
2. A cell as in Claim 1, wherein the polymeric matrix
15 comprises ethylene oxide in combination with acrylate groups.
3. A cell as in Claim 1, wherein the transparent electrode
comprises indium tin oxide.
- 20 4. A cell as in Claim 1, wherein the inorganic ion salt is
selected from the group consisting of LiClO_4 , LiI , LiSCN , LiBF_4 , LiAsF_6 ,
 LiCF_3SO_3 , LiPF_6 .
- 25 5. A cell as in Claim 1, wherein the electrolyte solvent
comprises an organic carbonate and a glyme.
6. A cell as in Claim 1 wherein the non-aqueous electrolytic
solvent is selected from the group consisting of propylene carbonate, ethylene
carbonate, γ -butyrolactone, tetrahydrofuran, glyme, diglyme, triglyme, tetraglyme,
30 dimethylsulfoxide, dioxolane, and sulfolane.

7. A cell as in Claim 1 wherein the redox couple comprises LiI and I₂.
8. A method of fabricating a photoelectrochemical cell which
5 comprises of the steps of:
 providing a current collector;
 securing a semiconductor on one side to the current collector;
 providing a transparent electrode; and
 forming a transparent single phase, solid solvent-containing
10 electrolyte by coating either (1) the other side of the semiconductor or (2) a side
of the transparent electrode with a composition containing a non-aqueous
electrolytic solvent and at least one solid matrix-forming monomer and curing the
composition to form the transparent solid solvent-containing electrolyte that is
15 positioned between the semiconductor and the transparent electrode, wherein the
solid electrolyte further comprises a redox couple and an inorganic ion salt.
9. A method as in Claim 8, wherein the polymeric matrix
comprises ethylene oxide in combination with acrylate groups.
10. A method as in Claim 8, wherein the at least one solid
20 matrix-forming monomer is selected from the group consisting of propylene oxide,
ethyleneimine, epichlorohydrin, ethylene succinate, and an acryloyl-derivatized
polyalkylene oxide containing an acryloyl group of the formula CH₂=CR'C(O)O-
wherein R' is hydrogen or lower alkyl of from 1-6 carbon atoms.
-
11. A method as in Claim 8, wherein the transparent electrode
25 comprises indium tin oxide.
12. A method as in Claim 8, wherein the inorganic ion salt is
30 selected from the group consisting of LiClO₄, LiI, LiSCN, LiBF₄, LiAsF₆,
LiCF₃SO₃, and LiPF₆.

13. A method as in Claim 8, wherein the electrolyte solvent comprises an organic carbonate and a glyme.

14. A method as in claim 8, wherein the non-aqueous electrolytic solvent is selected from the group consisting of propylene carbonate, ethylene carbonate, γ -butyrolactone, tetrahydrofuran, glyme, diglyme, triglyme, tetraglyme, dimethylsulfoxide, dioxolane, and sulfolane.

15. A method as in Claim 8 wherein the redox couple comprises LiI and I₂.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 96/13132

A. CLASSIFICATION OF SUBJECT MATTER IPC 6 H01G9/20				
According to International Patent Classification (IPC) or to both national classification and IPC				
B. FIELDS SEARCHED Minimum documentation searched (classification system followed by classification symbols) IPC 6 H01G				
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched				
Electronic data base consulted during the international search (name of data base and, where practical, search terms used)				
C. DOCUMENTS CONSIDERED TO BE RELEVANT				
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.		
X	EP 0 492 858 A (IMPERIAL CHEMICAL INDUSTRIES) 1 July 1992 see page 3, line 37 - line 41 see page 5, line 46 - line 47 see page 6, line 15 - line 23 see page 6, line 34 - line 41 see page 7, line 36 - line 38 see page 7, line 47 - line 57 see page 8, line 37 - line 40 see page 10, line 36 - line 51 ---	1-15		
A	US 4 585 581 A (SKOTHEIM T.) 29 April 1986 ---			
A	US 4 925 751 A (SHACKLE D.R.) 15 May 1990 cited in the application -----			
<input type="checkbox"/> Further documents are listed in the continuation of box C. <input checked="" type="checkbox"/> Patent family members are listed in annex.				
* Special categories of cited documents :				
<table style="width: 100%; border: none;"> <tr> <td style="width: 50%; vertical-align: top; border: none;"> "A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier document but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed </td> <td style="width: 50%; vertical-align: top; border: none;"> "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. "&" document member of the same patent family </td> </tr> </table>			"A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier document but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. "&" document member of the same patent family
"A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier document but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. "&" document member of the same patent family			
Date of the actual completion of the international search <div style="text-align: center; font-weight: bold;">23 December 1996</div>		Date of mailing of the international search report <div style="text-align: center; font-weight: bold;">14. 01. 97</div>		
Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl, Fax (+ 31-70) 340-3016		Authorized officer <div style="text-align: center; font-weight: bold;">Goossens, A</div>		

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 96/13132

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-0492858	01-07-92	AU-B- 658848	04-05-95
		AU-A- 8968391	25-06-92
		CA-A- 2058104	22-06-92
		JP-A- 5182512	23-07-93

US-A-4585581	29-04-86	US-A- 4416959	22-11-83
		US-A- 4442185	10-04-84
		US-A- 4488943	18-12-84

US-A-4925751	15-05-90	CA-A- 2013763	26-10-90
		DE-D- 69025089	14-03-96
		DE-T- 69025089	04-07-96
		EP-A- 0396324	07-11-90
		ES-T- 2084000	01-05-96
		JP-A- 2306550	19-12-90
		US-A- 5011501	30-04-91
